

**Yee Lee Industrial Chemical Ltd.**

義利工業原料有限公司



22/F, Hing Yip Commercial Centre,  
280 Des Voeux Road Central, Hong Kong  
Tel: (852) 2545 2611 Fax: (852) 2544 2498  
E-mail: [info@yeelee.com](mailto:info@yeelee.com) Web: [www.yeelee.com](http://www.yeelee.com)

## **HTE (High Temperature Elongation) Copper Foil**

Item	Unit	Specification Value						Test Method
Nominal Thickness	μm	9	12	15	18	35	70	IPC-TM-650
	oz	1/4	1/3	3/7	1/2	1	2	IPC-TM-650
Thickness by Weight	g/m <sup>2</sup>	76±5%	107±5%	125±5%	153±5%	285±5%	585±5%	IPC-TM-650
Purity	%	≥99.8	≥99.8	≥99.8	≥99.8	≥99.8	≥99.8	IPC-TM-650

The information contained herein is correct to the best of our knowledge. The recommendation or suggestion contained in this bulletin is made without guarantee or representation as to result. We suggest that you evaluate these recommendation and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.

Jan, 2017